



ICC ESR-2503
L.A. RR#: 25550

Roof Pavers Spec

AVM System 502 Aussie Membrane II

2-Part Heavy Duty Below Grade Bituminous Waterproofing Membrane

Sections 071000 / 071400 / 071416
Fluid Applied Waterproofing

Product Name

Aussie Membrane II
AVM System 502

Manufactured by

AVM Industries, Inc.
8245 Remmet Ave, Canoga Park, CA 91304
888.414.1041 818.888.0050
www.avmindustries.com

Product Description

The AVM AUSSIE MEMBRANE II is a 2-part waterproof, brown rubber/bitumen liquid emulsion with excellent adhesion, which dries to a tough, black seamless flexible waterproof membrane. The AUSSIE MEMBRANE II is a thixotropic cold-applied bitumen emulsion with added rubber latex. It exhibits excellent elongation and recovery properties.

Where to Use

Roofs and Decks with Pavers: Complete waterproofing system for wood or concrete decks where the Aussie membrane II is the primary waterproofing membrane over living spaces with pavers or pedestal paver systems scheduled to be installed over the Aussie II waterproofing system.

Important note: For Green Roof Systems" please refer to the "Green Roof Systems" Spec Data Sheet.

Warranty

AVM Industries will warranty the installed membrane for a period of five (5) years. Longer warranties are also available. For complete warranty details, contact AVM Industries or consult with your applicator.

Delivery, Storage, and Handling

- Delivery of all the AVM System 502 materials to the job site must be in their original sealed containers, with manufacturer's name and label intact.
- Handle and store containers in accordance with printed instructions.
- Store at temperatures between 50°F and 90°F. Do not store materials in direct sunlight or where they may be damaged by water or rain.
- Failure to comply with the recommended storage conditions may result in premature deterioration of the product. For specific storage advice, please contact AVM Industries and/or its representatives.
- Keep all materials out of the reach of children.
- If irritation occurs during use, liberally flush affected areas with water. If irritation continues, see a physician immediately.

Project Conditions

- All surfaces to which the AUSSIE MEMBRANE II is applied to must be sound and stable, with an even finish and free from dust, loose debris, grease, curing agents, etc.

- The AUSSIE MEMBRANE II may be applied to damp but not waterlogged surfaces (Green Concrete)
- Do not apply materials at temperatures below 50°F and falling or if precipitation is imminent. Do not apply materials in direct sunlight at temperatures above 90°F or rising.
- Warn personnel against hazards of materials to skin and eyes. Note other hazardous conditions on the job that might require special protective gear and or any other special protective or safety procedures.
- Protect adjacent surfaces which could be damaged during the application procedure.
- This system must not be used to cover Expansion Joints.

System Application

Read the AVM System 502 Installation Instructions Prior to Installation. Application instructions vary based on application surfaces. Following are common application procedures only. For specific application procedures, download the appropriate installation instructions.

Preparation

- Make sure concrete surfaces are even without holes, gaps, etc. Make sure substrate has no cracks larger than 1/16" wide. If applying over plywood substrates, make sure it's exterior grade plywood, min 5/8" thick, (No OSB), its sound and fully blocked.
- Over concrete, if necessary, apply a thin slurry coat using AVM Crete 6200. Over plywood, apply AVM Crete 6400 at a min of 1/4" thick to all plywood surfaces.
- Apply a 1"x1" mortar cant at 450 at horizontal-to-vertical transitions. Then apply a detailed coat. (See details)
- Mixing: Mix the product in the drum or tote by circulating it through the pump. For drums, mix each a min of 10 minutes, for totes, mix each a min of 15 minutes! Do not add or dilute with water!
- Priming: Spray a thin coat of the Aussie membrane II without the accelerator as primer when needed.

Membrane Installation

Accelerator: Pour the 55 Lbs of salt into 32-35 gallons of water and mix well.

Spray: Don't forget to pre-mix contents in drum or tote! (See installation instructions)

Spray product with accelerator until desired thickness is achieved. Membrane should be 270 Mils dry with 2 Mat 800 fabrics inserted for reinforcement. If less, consult with engineer or AVM. (See Min Thickness Table and details for more information) Spraying ratio is measured by volume and should be 90% bitumen to 10% salt water. (For every gallon of salt water, spray 9 gallons of bitumen) Once the membrane is dry to the touch, check for proper thickness. If necessary, spray another coat. Walls: 2nd Coat on vertical walls must be applied within 2-3 minutes. Otherwise wait until the next day before applying the 2nd coat. Floors: Apply 1st coat from lowest parts to highest parts of the floor. (So salt water will not flow onto unsprayed areas!) To apply a 2nd coat, evacuate the water before spraying the second coat and spray the second coat within 2-3 minutes of the first coat. Otherwise wait until the next day between coats.

Quality Control

- Visually inspect all coated surfaces to ensure a full and proper coating application, especially at corners, drainage footings and other hard-to-reach areas.
- All unsatisfactory areas shall be repaired prior to final acceptance.

Protection of Installed Work

- The completed section shall be protected for the first 24 hours after application or until the surface is sufficiently cured. (The amount of drying time may vary depending on temperature and humidity conditions)
- Always protect the waterproofing from possible damage. The Roof Pavers System includes Protective Panels and/or special drainage boards. All are integral to the system. Refer to the job's specs and Installation Instructions for more info.

Availability and Cost

Contact AVM Industries or your approved applicator for pricing and availability.

Technical Services

Technical services are available by contacting our offices at: 888.414.1041 or 818.888.0050 or visit www.avmindustries.com

System Specifications

See next page.

The following coverages are based on controlled tests. Actual coverages may vary.

Technical Information

Color	Emulsion: Dark brown. Membrane: black	
Specific Gravity	1 gr/cm ²	
Solid Content	60% +/- 2%	
Flash Point	Non-flammable	
Service Temperature	15°F-140°F (-10°C to +60°C)	
Application Temperature	40°F-100°F (+5°C to 40°C)	
Heat Stability	>194°F (>90°C)	ASTM D 2939
Cold Flexibility	-4°F (-20°C)	ASTM D 522
Low Temperature Flexibility and Crack Bridging	Pass, Conducted @ -15°F (-26°C)	ASTM D 836
Tensile Strength	>0.1 MPa (>14.2 psi)	ASTM D 412
Elongation at break	>1200%	ASTM D 412
Resistance to water pressure	>1 atm, 24 hr (>14.7 psi, 24 hr)	DIN 52123
Water vapor permeance	0.35 Perms	ASTM E 96
Recovery (at 800-900% elongation)	>85%	ASTM D 412
Creep At 212°F (100°C)	No Creep	DIN 52123
Resistance to Standing Water	Passed	ASTM D 2939
Bacterial Attack in soil 30 days @ 105°F (40°C)	Passed	ASTM D 3083
VOC (Volatile Organic Content)	20 Grams/Liter	
Crack bridging	>3/16" (>5mm)	IS 1731
Approvals / Certifications	ICC, LARR, ISO 9002, Green Label, I.Q. Net (International Certification Network)	

Mixing / Spraying Information


Mixing Ratio	Accelerator (Salt water): Pour the 55 lbs of salt into 32-35 gallons of water
Spraying Ratio	1 Gallon accelerator (salt water) to 9 gallons of bitumen

For membrane thickness and drainage board requirements refer to the "Aussie II Min Thickness Table"

Coverage Tables (for U.S. and Metric Measurements)

To Get	60 Mills Dry	90 Mills Dry	100 Mills Dry	120 Mills Dry	160 Mills Dry	180 Mills Dry	240 Mills Dry	270 Mills Dry
Apply	100 Mills Wet	150 Mills Wet	160 Mills Wet	200 Mills Wet	160 Mills Wet	300 Mills Wet	400 Mills Wet	450 Mills Wet
For 100 sqft	5.75 Gallons	8.75 Gallons	9.5 Gallons	11.5 Gallons	15 Gallons	17.25 Gallons	23 Gallons	26.25 Gallons
To Get	1.5 mm Dry	2.25 mm Dry	2.5 mm Dry	3.0 mm Dry	4.0 mm Dry	4.5 mm Dry	6.0 mm Dry	6.75 mm Dry
Apply	2.4 mm Wet	3.6 mm Wet	4.0 mm Wet	4.8 mm Wet	6.4 mm Wet	7.2 mm Wet	9.6 mm Wet	10.8 mm Wet
For M ²	2.4 kg/m ²	3.6 kg/m ²	4.0 kg/m ²	4.8 kg/m ²	6.5 kg/m ²	7.3 kg/m ²	9.6 kg/m ²	10.8 kg/m ²

Item / Component	Packaging	Approx Shipping Weights	VOC
AVM Primer 500	2.0/5.0 gal. pails	2.0/5.0 gal. 15/39 lbs.	15 Grams/Liter
AVM Aussie II	264 Gal Totes	264.0 gal. 2,200 lbs / 1,000 kg (1-Ton)	19 Grams/Liter



NOTE:
 - FOR PAVERS OVER PEDESTALS INSTALLATION USE MIN 1/4" RIGID PROTECTION BOARD OR RIGID INSULATION. AT PEDESTRIAN TRAFFIC, 40 PSI INSULATION IS ACCEPTABLE, RECOMMEND 60 PSI. AT VEHICULAR TRAFFIC, USE MIN. 60 PSI. CHANNELLED RIGID INSULATION MIGHT BE USED IN LIEU OF DRAINAGE BOARD.
 - REFER TO SPECIFICATIONS FOR MEMBRANE THICKNESS REQUIREMENTS.

NOTE: FOR PROPER MEMBRANE THICKNESS AND APPROPRIATE PROTECTION BOARDS, REFER TO AUSSIE II "MIN. THICKNESS TABLE".

For a complete list of details in CAD or PDF, please visit our website at www.avmindustries.com.

AVM Industries, Inc.
 8245 Remmet Ave, Canoga Park, CA 91304
 888.414.1041 818.888.0050

Quality Waterproofing Products



www.avmindustries.com